

CORROSION

GENERAL INTRODUCTION

TECHNICAL BULLETIN CTB-1

Rev 3, November 2003

This issue supersedes all previous issues

INTRODUCTION

While Architects, Roof Plumbers and Builders may not need to fully understand the chemistry and mechanics of metallic corrosion, there should be an awareness of the many materials design, specification and installation combinations that have a potential to cause unsatisfactory material performance.

The most common factor leading to eventual material replacement is time. This statement recognises that all materials eventually suffer from some form of deterioration. While premature replacement of brittle building materials can be initiated by impact damage, and timber may rot or suffer from termite attack, the common reason for failure of metal products, is eventual corrosion.

Corrosion may be defined as the destruction or deterioration of a material because of a reaction with its environment. For steel, it is often the case of the iron endeavouring to return to the original hydrated iron oxide or iron oxide state. Although many other metals form their oxide when corrosion occurs, "rusting" is a term reserved for the corrosion of iron and steel.

All environments are corrosive to some degree. Such reactions are generally governed by the available moisture within the specific environment which can allow an otherwise benign environment to greatly assist the onset of corrosion mechanisms. Further contamination of the environment where acid products may exist or be derived from industrial or marine contamination, will only serve to expedite such reactions leading to the premature demise of the material.

BlueScope Steel Limited has endeavoured to take advantage of the natural galvanic protection associated with preferential corrosion of specific metallic materials when placed in contact with less active metals.

To achieve this effect, metallic coatings are applied to steel substrates for the purpose of increasing the corrosion resistance of the steel product. Some examples of applications for which metallic coatings are commonly applied to steel, for the prime purpose of providing corrosion protection are as follows:

1. Hot dipped zinc/aluminium coating (*ZINCALUME® zinc/aluminium alloy-coated steel*) used for roofing, walling, rain water goods and numerous fabricated articles for interior/exterior use.
2. Hot dipped zinc coating (*galvanized*) used for structural purlin fabrication, fence posts, concrete decking and numerous articles for interior/exterior use within the building industry.
3. Electro deposited tin coating used in the canning industry.

There are two different types of metallic coatings; "active" (*or sacrificial*) coatings and "noble" (*or cathodic*) coatings. The terms active and noble indicate whether the metallic coatings are active (*will corrode*) or noble (*will not corrode*) compared with steel. Galvanized or ZINCALUME® steel coatings are active. Hot-dipped lead/tin coatings are noble, while tin coatings constitute a special case.

Tin is cathodic to steel on the outside of a tin plated steel container but usually active to steel on the inside. That is whether the corrosion potential of the metallic coating is more negative or more positive than the corrosion potential of steel in the same environment.


At defective areas in an active metal coating, the metal coating will corrode and sacrifice itself in an attempt to protect the steel substrate, where a defect in a noble metal coating will cause the steel substrate to corrode in an attempt to protect the metal coating. Noble metal coatings therefore must contain minimal porosity which may indicate a thick coating requirement or carefully controlled process parameters.

Two important qualities of an active metal coating are:

- a) essential corrosion resistance.
- b) ability to corrode in a controlled manner to sacrificially protect the steel base.
*(Sacrificial protection is also commonly referred to as galvanic protection.
Refer CTB-2)*

When a metal is placed in a corrosive environment, cathodic and anodic areas form on the surface. These areas form localised corrosion cells and are usually microscopic in size. The chemically active sites such as surface defects, cracks in surface films, or grain (*spangle*) boundaries are where the corrosion or anodic reactions are initiated.

Metal dissolution (*or corrosion*) is expected to occur at these sites according to the following anodic reaction:-



When considering the surfaces of bare metals, cathodes are typically found at sites of lesser chemical activity such as within grain interiors. For corrosion to occur, the electrons made available from dissolution of the anodic metal are consumed by the adjacent cathodic reaction. The two main reactions at the cathodic site are:-

Reduction of hydrogen ions to produce hydrogen gas which will predominate in acid solutions:



Or, in near neutral environments dissolved oxygen is reduced to form hydroxide by the following reaction:



The information and advice contained in this Bulletin is of a general nature only, and has not been prepared with your specific needs in mind. You should always obtain specialist advice to ensure that the materials, approach and techniques referred to in this Bulletin meet your specific requirements.

BlueScope Steel Limited makes no warranty as to the accuracy, completeness or reliability of any estimates, opinions or other information contained in this Bulletin, and to the maximum extent permitted by law, BlueScope Steel Limited disclaims all liability and responsibility for any loss or damage, direct or indirect, which may be suffered by any person acting in reliance on anything contained in or omitted from this document.

ZINCALUME® is a registered trade mark of BlueScope Steel Limited.
BlueScope is a trade mark of BlueScope Steel Limited.

Please ensure you have the current Technical Bulletin as displayed at www.bluescopesteel.com.au

BlueScope Steel

Copyright© 2003 BlueScope Steel Limited
BlueScope Steel Limited ABN 16 000 011 058
BlueScope Steel (AIS) Pty Ltd ABN 19 000 019 625



AUSTRALIA	SYDNEY	Telephone: (02) 9795 6700
	MELBOURNE	Telephone: (03) 9586 2222
	BRISBANE	Telephone: (07) 3845 9300
	ADELAIDE	Telephone: (08) 8243 7333
	PERTH	Telephone: (08) 9330 0666

OVERSEAS	BlueScope Steel (Malaysia) Sdn Bhd	Telephone: (603) 3250 8333
	BlueScope Steel (Thailand) Limited	Telephone: (66 38) 685 710
	PT BlueScope Steel Indonesia	Telephone: (62 21) 570 7564
	BlueScope Steel Southern Africa (Pty) Limited	Telephone: (27 21) 555 4265

